

**TEST REPORT**

DATE: 05-19-2023

Page 1 of 1

TEST NUMBER: 0296768

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	ASTM F387 Standard Test Method for Measuring Thickness of Resilient Floor Covering with Foam Layer
-----------------------	--



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	1901-2134 Mission Bay 7"x48" (4.5)
LOT NUMBER	Batch: 221129-11991
CONSTRUCTION	SPC

**GENERAL PRINCIPLE**

The total thickness of a resilient flooring material is determined through measurements made using a .250 inch presser foot and a dial micrometer. The average of 5 total measurements is reported as the average total thickness.

**TEST RESULTS**

		THICKNESS
	SPECIMEN 1	0.183 Inch
	SPECIMEN 2	0.184 Inch
	SPECIMEN 3	0.182 Inch
	SPECIMEN 4	0.183 Inch
	SPECIMEN 5	0.183 Inch
AVERAGE TOTAL THICKNESS		0.183 Inch

APPROVED BY: \_\_\_\_\_



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc. shall not be used under any circumstance in advertising to the general public.

