

TEST REPORT

DATE: 05-19-2023 Page 1 of 1 TEST NUMBER: 0296768

CLIENT Urban Surfaces

	ASTM F410 (Modified per ASTM F3261) Standard Test Method for
TEST METHOD CONDUCTED	Wear Layer Thickness of Resilient Floor Coverings by Optical
	Measurement



DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	1901-2134 Mission Bay 7"x48" (4.5)	
LOT NUMBER	Batch: 221129-11991	
CONSTRUCTION	SPC	

GENERAL PRINCIPLE

The thickness of the wear layer of resilient non-textile floor coverings is determined by microscopic optical measurement. The specimen is examined in five areas and measurements are made on the outer most layer of the composite material. The measurements are recorded to the .0001 inch and averaged. Only the highest thickness values are reported per ASTM F3261, avoiding values from any non-embossed areas.

TEST RESULTS

	THICKNESS	
SPECIMEN 1	0.0068 inch	
SPECIMEN 2	0.0073 inch	
SPECIMEN 3	0.0062 inch	
SPECIMEN 4	0.0065 inch	
SPECIMEN 5	0.0070 inch	
·		

AVERAGE TOTAL THICKNESS	0.0068 Inch	6.8 mil

APPROVED BY:

Lang atluny

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us