

**TEST REPORT**

DATE: 05-19-2023

Page 1 of 1

TEST NUMBER: 0296768

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	ASTM F925 (Regular) Standard Test Method for Resistance to Chemicals of Resilient Flooring
-----------------------	--



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	1901-2134 Mission Bay 7"x48" (4.5)
LOT NUMBER	Batch: 221129-11991
CONSTRUCTION	SPC

TEST RESULTS

5 MINUTE RATINGS				24 HOUR RATINGS		
STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid	0	0	0	0	0	0
70% Isopropyl Alcohol	0	0	0	0	0	0
Mineral Oil	0	0	0	0	0	0
5% Sodium Hydroxide	0	0	0	0	0	0
5% Hydrochloric Acid	0	0	0	0	0	0
5% Ammonia	0	0	0	0	0	0
Bleach	0	0	0	0	0	0
5% Phenol	0	0	0	0	0	0
Gasoline	0	0	0	0	0	0
5% Sulfuric Acid	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0
Olive Oil	0	0	0	0	0	0

RATING KEY	
0	No change (---)
1	Slight change
2	Moderate change
3	Severe change

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.