

**TEST REPORT****DATE: 06-24-2022****Page 1 of 1****TEST NUMBER: 0287733**

CLIENT	Urban Surfaces
---------------	----------------

TEST METHOD CONDUCTED	NALFA 3.12, 3.13, 3.14 Determination of Flatness, Openings and Ledging
------------------------------	--



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	4001 Camden
LOT NUMBER	Batch: 220131-10981
CONSTRUCTION	Laminate Flooring

GENERAL PRINCIPLE

The submitted goods were measured to determine geometrical values for flatness, openings and ledging when applied together. All values listed are in mm.

TEST RESULTS

CHARACTERISTIC	VALUE (mm)
3.12 Width Flatness	Max:0.194 (0.099 %)/ Avg:0.169 (0.087 %) - Concave
3.12 Length Flatness	Max:0.241 (0.020 %)/ Avg:0.186 (0.015 %) - Concave
3.13 Openings Between Elements	Max:0.167 / Avg: 0.091
3.14 Height Difference Between Elements (Ledging)	Max:0.122 / Avg: 0.083

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.