

**TEST REPORT**

DATE: 06-24-2022

TEST NUMBER: 0287733

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	NALFA 3.4 Cleanability-Stain Resistance
-----------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	4001 Camden
LOT NUMBER	Batch: 220131-10981
CONSTRUCTION	Laminate Flooring

GENERAL PRINCIPLE

This test measures both the ease of cleanability and stain resistance of high pressure decorative laminate by common household stains. The staining agents are removed and graded by the ease of removal procedure. If the agent cannot be removed and is left as a stain, the stain is rated and reported as such.

TEST RESULTS

STAINING AGENT	REMOVAL SCORE	STAIN RESISTANCE
Distilled Water	0	No Effect
50:50 Ethyl Alcohol	0	No Effect
Acetone	0	No Effect
Household Ammonia	0	No Effect
10% Citric Acid	0	No Effect
Vegetable Oil	0	No Effect
Fresh Coffee	0	No Effect
Fresh Tea	0	No Effect
Catsup	0	No Effect
Yellow Mustard	0	No Effect
10% Providone Iodine	0	No Effect
Black Marker Ink	3	No Effect
#2 Pencil	0	No Effect
Wax Crayon	0	No Effect
Black Shoe Polish	2	No Effect
TOTAL REMOVAL SCORE	5	

*** Meets NALFA specified criteria for usage Levels 1, 2, 3 and 4.**

Class 1 RESIDENTIAL	Class 2 LIGHT COMMERCIAL	Class 3 COMMERCIAL	Class 4 HEAVY COMMERCIAL
< 20 - No More than Slight Effect	< 20 - No More than Slight Effect	< 20 No More than Slight Effect	< 20 No More than Slight Effect

Cleaning Agents	
0	Water
1	Mild Detergent
2	Baking Soda w/Brush
3	Acetone
4	Bleach
5	Stain Remains

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.