



TEST REPORT

DATE: 06-24-2022

TEST NUMBER: 0287733

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	NALFA 3.6 Small Ball (Dart) Impact Resistance
------------------------------	-----------------------------------------------



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	4001 Camden
LOT NUMBER	Batch: 220131-10981
CONSTRUCTION	Laminate Flooring

GENERAL PRINCIPLE

This test measures the ability of a laminate flooring to resist fracture due to impact by a small diameter ball/dart (25 grams) falling onto the surface of the unrestricted laminate floor sample. Drops are conducted in incremental heights until the surface of the material is fractured. The submitted material was tested according to the NALFA requirements using the proper underlayment.

TEST RESULTS

MAXIMUM HEIGHT TO ACHIEVE FRACTURE OF SURFACE LAYER	RESULT
WITH UNDERLAYMENT	500 mm (19.7 inch)

*** Meets NALFA specified criteria for usage Levels 1, 2, 3 and 4.**

Class 1 RESIDENTIAL	Class 2 LIGHT COMMERCIAL	Class 3 COMMERCIAL	Class 4 HEAVY COMMERCIAL
> 200 mm (7.9 inch)	> 200 mm (7.9 inch)	> 350 mm (13.8 inch)	> 500 mm (19.7 inch)

APPROVED BY:

Gary A. Gury

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.