

**TEST REPORT****DATE: 03-28-2023****Page 1 of 1****TEST NUMBER: 0295476**

<b>CLIENT</b>	Urban Surfaces
---------------	----------------

<b>TEST METHOD CONDUCTED</b>	ASTM D2047 James Machine - Coefficient of Friction on Flooring Material
------------------------------	---



DESCRIPTION OF TEST SAMPLE	
<b>IDENTIFICATION</b>	2906 Chestnut 7"x48"
<b>LOT NUMBER</b>	Batch: 210609-10515

**GENERAL PRINCIPLE**

This test was used to measure the relative static coefficient of friction by using the James Machine.

**TEST RESULTS**

<b>TEST ENVIRONMENT</b>	69° F 50% Relative Humidity
-------------------------	-----------------------------

Sensor Materials	Dry
Leather	0.69

APPROVED BY: \_\_\_\_\_



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc. shall not be used under any circumstance in advertising to the general public.

