

**TEST REPORT**

DATE: 03-28-2023

Page 1 of 1

TEST NUMBER: 0295476

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	ASTM F2199 Standard Test Method for Determining Dimensional Stability and Curling Properties of Resilient Floor Tile after Exposure to Heat
-----------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	2906 Chestnut 7"x48"
LOT NUMBER	Batch: 210609-10515

GENERAL PRINCIPLE

This test method is intended for use in determining the linear change of resilient flooring after being exposed to heat. The dimensional change over 12 inches is reported as the dimensional stability.

TEST RESULTS

Replicate	Direction	Temp	Dimensional Change	Initial Curl	Final Curl
#1	Length	70° C	+0.002 inch/12 inches (+0.02%)	0.00 inch (0.00 mm)	0.04 inch (1.02 mm)
	Width	70° C	0.000 inch/12 inches (0.00%)		
#2	Length	70° C	+0.002 inch/12 inches (+0.02%)	0.00 inch (0.00 mm)	0.03 inch (0.76 mm)
	Width	70° C	+0.005 inch/12 inches (+0.04%)		
#3	Length	70° C	+0.003 inch/12 inches (+0.02%)	0.00 inch (0.00 mm)	0.04 inch (1.02 mm)
	Width	70° C	0.000 inch/12 inches (0.00%)		

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.