

TEST REPORT

DATE: 03-28-2023

Page 1 of 1

TEST NUMBER: 0295476

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	ASTM F3261 Thickness Swell
-----------------------	----------------------------



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	2906 Chestnut 7"x48"
LOT NUMBER	Batch: 210609-10515

This test measures the ability of flooring to resist edge thickness increases after being exposed to distilled water. Two 6" x 6" specimens are cut and the thickness is calculated using a compressometer. The two samples are submerged one inch below the water line in 70° F distilled water for 24 hours and then removed and re-measured. The thickness swell is calculated as a percentage of the original thickness.

TEST RESULTS

	THICKNESS SWELL	PERCENTAGE SWELL
SPECIMEN 1	0 Inch	0%
SPECIMEN 2	0 Inch	0%

APPROVED BY:

Gary A. Curry

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.