

## **TEST REPORT**

**DATE: 03-28-2023** Page 1 of 1 TEST NUMBER: 0295476

**CLIENT** Urban Surfaces

TEST METHOD CONDUCTED

ASTM F387 Standard Test Method for Measuring Thickness of Resilient Floor Covering with Foam Layer

DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	2906 Chestnut 7"x48"	
LOT NUMBER	Batch: 210609-10515	

## **GENERAL PRINCIPLE**

The total thickness of a resilient flooring material is determined through measurements made using a .250 inch presser foot and a dial micrometer. The average of 5 total measurements is reported as the average total thickness.

## **TEST RESULTS**

	THICKNESS
SPECIMEN 1	0.201 Inch
SPECIMEN 2	0.201 Inch
SPECIMEN 3	0.200 Inch
SPECIMEN 4	0.201 Inch
SPECIMEN 5	0.202 Inch

AVERAGE TOTAL THICKNESS	0.201 Inch

APPROVED BY:

TESTING NAMP LAB CODE 100297-0

Lary aslowry

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the producttested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples testedand is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc. shall not be used under any circumstance in advertising to the general public.



714 Glenwood Place Dalton, GA 30721 706-226-3283 Fax: 706-226-6787 protest@optilink.us