

TEST REPORT

CLIENT Urban Surfaces

| TEST METHOD CONDUCTED | ISO | 24337 | Laminate | Floor | Coverings | - | Determination | of |
|-----------------------|-----------------------------|-------|----------|-------|-----------|---|---------------|----|
| IEST WEIHOD CONDUCTED | Geometrical Characteristics | | | | | | | |



| DESCRIPTION OF TEST SAMPLE | | | | | |
|----------------------------|----------------------|--|--|--|--|
| IDENTIFICATION | 2906 Chestnut 7"x48" | | | | |
| LOT NUMBER | Batch: 210609-10515 | | | | |

GENERAL PRINCIPLE

The submitted goods were measured to determine geometrical values for size, squareness, straightness, height deviations, and gapping when applied together. All values listed are in mm.

TEST RESULTS

| CHARACTERISTIC | | | | VALUE (mm) | | | | | | |
|------------------------------------|--------|-------|---------|------------|-------|-------|--------|--------|--|--|
| Thickness | | | | 5.177 | | | | | | |
| Length | | | | 1217.394 | | | | | | |
| Width | | | 178.990 | | | | | | | |
| Straightness | itness | | | | 0.062 | | | | | |
| Squareness (out of square) | | | Max: | 0.221 | | | Avg: | 0.145 | | |
| Openings Between Elements | | | Max: | 0.141 | | | Avg: | 0.086 | | |
| Height Difference Between Elements | | Max: | 0.148 | | | Avg: | 0.097 | | | |
| Width Flatness | Max: | 0.174 | 0.09 | 7% | Avg | 0.138 | 0.077% | Convex | | |
| Length Flatness | Max: | 0.237 | 0.01 | 9% | Avg | 0.179 | 0.015% | Convex | | |

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us

Lang aslung