

TEST REPORT

DATE: 01-14-2025 TEST NUMBER: 0313881

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	NALFA 3.4 Cleanability-Stain Resistance
-----------------------	---

DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	Timber Haus	
CONSTRUCTION	8mm + 1mm Eco Pad Laminate Water Resistant	
BACKING	1mm Eco Pad	

GENERAL PRINCIPLE

This test measures both the ease of cleanability and stain resistance of high pressure decorative laminate by common household stains. The staining agents are removed and graded by the ease of removal procedure. If the agent cannot be removed and is left as a stain, the stain is rated and reported as such.

TEST RESULTS

STAINING AGENT	REMOVAL SCORE	STAIN RESISTANCE
Distilled Water	0	No Effect
50:50 Ethyl Alcohol	0	No Effect
Acetone	0	No Effect
Household Ammonia	0	No Effect
10% Citric Acid	0	No Effect
Vegetable Oil	0	No Effect
Fresh Coffee	0	No Effect
Fresh Tea	0	No Effect
Catsup	0	No Effect
Yellow Mustard	2	No Effect
10% Povidone Iodine	0	No Effect
Black Marker Ink	2	No Effect
#2 Pencil	0	No Effect
Wax Crayon	0	No Effect
Black Paste Shoe Polish	2	No Effect
TOTAL REMOVAL SCORE	6	

^{*} Meets NALFA specified criteria for usage Levels 1, 2, 3 and 4.

Class 1 RESIDENTIAL	Class 2 LIGHT COMMERCIAL	Class 3 COMMERCIAL	Class 4 HEAVY COMMERCIAL
< 20 - No More than Slight	< 20 - No More than Slight	< 20 No More than Slight	< 20 No More than Slight
Effect	Effect	Effect	Effect

Cleaning Agents

0 Water

1 Mild Detergent

2 Baking Soda w/Brush

3 Acetone

4 Bleach

5 Stain Remains

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us