

TEST REPORT

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	ASTM F1515 Measuring Light Stability of Resilient Flooring by Color Change
-----------------------	--

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Zeno PVC Free
CONSTRUCTION	PVC Free 3mm 7x48

GENERAL PRINCIPLE

The test specimens are exposed to accelerated light via xenon light using the standard irradiance as listed in the method. The materials are read using a spectrophotometer for the baseline color value and then read after 100, 200, and 300 hours of exposure. The Delta E is listed to show the color value change resulting from each exposure.

TEST RESULTS

	DELTA E (△E) Rating	Gray Scale Rating
100 AFU Exposed Sample Average	0.34	5.0
200 AFU Exposed Sample Average	0.97	4.5
300 AFU Exposed Sample Average	1.01	4.5
MAXIMUM RATING	1.01	5.0

Test requirements of < 8.0 Delta E were met by the tested samples.

	AATCC RATING KEY		
5	No change		
4	Slight change		
3	Noticeable change		
2	Considerable change		
1	Severe change		

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us