

TEST REPORT

CLIENT	Urban Surfaces
--------	----------------

	ASTM F2	199 St	andard	Test Method	d fo	r Determii	ning D	imen	sional
TEST METHOD CONDUCTED	'		•	Properties	of	Resilient	Floor	Tile	after
	Exposure	? 10 HE	eat						

DESCRIPTION OF TEST SAMPLE			
IDENTIFICATION	Zeno PVC Free		
CONSTRUCTION	PVC Free 3mm 7x48		

GENERAL PRINCIPLE

This test method covers the determination of the change in linear dimensions of resilient floor tile/plank products after exposure to heat aging and reconditioning to ambient temperature. This method allows the measure of curling or doming that can occur after a specimen has been exposed to heat aging and reconditioned back to ambient temperature.

TEST RESULTS

SAMPLE 1

Direction	Temperature	Linear Change	% Change	Initial	Final I	nitial Domin	inal Doming
Length	80° C	-0.003 in/foot	-0.02 %	12.203 in	12.200 in	0.02	0.05 in
Width	80° C	0.002 in/foot	0.01 %	6.991 in	6.992 in		

SAMPLE 2

Direction	Temperature	Linear Change	% Change	Initial	Final I	nitial Domin	inal Doming
Length	80° C	0.000 in/foot	0.00 %	12.185 in	12.185 in	0.02	0.05 in
Width	80° C	0.000 in/foot	0.00 %	6.992 in	6.992 in		

SAMPLE 3

Direction	Temperature	Linear Change	% Change	Initial	Final I	nitial Domin	inal Doming
Length	80° C	0.000 in/foot	0.00 %	12.177 in	12.177 in	0.03	0.05 in
Width	80° C	0.000 in/foot	0.00 %	6.992 in	6.992 in		

AVG Length	0.01 %	MAX Length	0.02 %
AVG Width	0.00 %	MAX Width	0.01 %

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products.

This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us