

TEST REPORT

DATE: 01-22-2025
Page 1 of 1
TEST NUMBER: 0313924

| | |
|---------------|----------------|
| CLIENT | Urban Surfaces |
|---------------|----------------|

| | |
|------------------------------|--|
| TEST METHOD CONDUCTED | ASTM F925 Standard Test Method for Resistance to Chemicals of Resilient Flooring |
|------------------------------|--|

| DESCRIPTION OF TEST SAMPLE | |
|----------------------------|-------------------|
| IDENTIFICATION | Zeno PVC Free |
| CONSTRUCTION | PVC Free 3mm 7x48 |


GENERAL PRINCIPLE

This test method provides a procedure for determining the resistance of resilient floor covering to surface deterioration when exposed to various chemical reagents. This test method is not intended as a staining test nor as a method to judge surface and appearance restoration of the sample after exposure to the chemical reagent.

TEST RESULTS

| | 5 MINUTE RATINGS | | | 24 HOUR RATINGS | | |
|-----------------------|------------------|----------------|--------------|-----------------|----------------|--------------|
| | SURFACE DULLING | SURFACE ATTACK | COLOR CHANGE | SURFACE DULLING | SURFACE ATTACK | COLOR CHANGE |
| 5% Acetic Acid | 0 | 0 | 0 | 0 | 0 | 0 |
| 70% Isopropyl Alcohol | 0 | 0 | 0 | 0 | 0 | 0 |
| Mineral Oil | 0 | 0 | 0 | 0 | 0 | 0 |
| 5% Sodium Hydroxide | 0 | 0 | 0 | 0 | 0 | 0 |
| 5% Hydrochloric Acid | 0 | 0 | 0 | 0 | 0 | 0 |
| 5% Ammonia | 0 | 0 | 0 | 0 | 0 | 0 |
| Bleach | 0 | 0 | 0 | 0 | 0 | 0 |
| 5% Phenol | 0 | 0 | 0 | 0 | 0 | 0 |
| Gasoline | 0 | 0 | 0 | 0 | 0 | 0 |
| 5% Sulfuric Acid | 0 | 0 | 0 | 0 | 0 | 0 |
| Kerosene | 0 | 0 | 0 | 0 | 0 | 0 |
| Olive Oil | 0 | 0 | 0 | 0 | 0 | 0 |

| RATING KEY | |
|------------|-----------------|
| 0 | No change (---) |
| 1 | Slight change |
| 2 | Moderate change |
| 3 | Severe change |

APPROVED BY: 

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, LLC, shall not be used under any circumstance in advertising to the general public.