

**TEST REPORT**

DATE: 07-06-2023

Page 1 of 1

TEST NUMBER: 0298457

CLIENT	Urban Surfaces
--------	----------------

TEST METHOD CONDUCTED	ASTM F386 Standard Test Method for Thickness of Resilient Flooring Materials Having Flat Surfaces
-----------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	UTREAD Urban Full Tread
COLOR	9565 Magnolia
LOT NUMBER	Batch No: 221011-11

GENERAL PRINCIPLE

The total thickness of a resilient flooring material is determined through measurements made using a .250 inch presser foot and a dial micrometer. The average of 5 total measurements is reported as the average total thickness.

TEST RESULTS

		THICKNESS
	SPECIMEN 1	0.343 Inch
	SPECIMEN 2	0.342 Inch
	SPECIMEN 3	0.344 Inch
	SPECIMEN 4	0.342 Inch
	SPECIMEN 5	0.341 Inch

AVERAGE TOTAL THICKNESS	0.342 Inch
-------------------------	------------

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.