

Technical Data Sheet





✓ MULTIFAMILY

✓ LIGHT COMMERCIAL

DESCRIPTION

An unlimited moisture vapor barrier and elastomeric membrane. Provides 100% moisture protection, no testing required. Before applying any adhesive, use Urban Surfaces' Infuse (encapsulator and primer).

APPROVED SUBSTRATES & SURFACES

- · Cementitious and anhydrite screeds.
- Concrete and radiant heated subfloors that do not exceed 85°F (30°C).

SUBSTRATE TESTING

RH [ASTM F2170]	No Testing Required (100% RH)
pH [ASTM F710]	No Testing Required (5-14 pH)
MVER [ASTM F1869]	No Testing Required
Porosity [ASTM F3191]	Must Pass, CSP 1+

SUBSTRATE & SURFACE PREPARATION

- **1.** All substrates must be prepared per ASTM F710 standards including, but not limited to the following:
 - Concrete floors must be dry, clean, smooth, flat, and structurally sound. They shall be free of any foreign materials that might prevent proper absorption, including dust, dirt, solvent, paint, wax, oil, grease, residual adhesive, adhesive removers, incompatible sealers, fire-retardant chemicals, fungicides, release agents, alkaline salts, excessive carbonation, laitance, mold, mildew, and curing, sealing, hardening or parting compounds, or unapproved mixtures
 - Fill all surface cracks, grooves, depressions, control joints and non-moving joints with moisture resistant patching and self-leveling compounds, allow to fully cure and correct high spots before application.
- **2.** The substrate, product (Infiniti), any adhesives, and flooring that follows must be acclimated in an enclosed building with the HVAC operational between 60-95°F (15.5-35°C), and between 30-65% relative humidity, for at least 72 hours before, during, and permanently after installation.
- When installing over radiant heated subfloors, turn the heat off for 24 hours before, during, and 24 hours after installation. Failure to turn the heat off may result in shortened working time of the adhesive. When turning radiant heat back on, raise it incrementally, not to exceed a change of more than 5 degrees per hour to a maximum of 85°F (29°C).

Precautionary Notes:

 An intact moisture vapor retarder must be present below the concrete (see ASTM E1745), must be fully cured (at least 45 days), porous (see ASTM F3191), without hydrostatic pressure or pressurized liquid from any source, and free of surface alkaline salt crystallization.

SUBSTRATE & SURFACE PREPARATION (continued)

- Concrete must be a minimum of 2,500 psi and without visible or standing water.
- Substrate must be porous per ASTM F3191.

APPLICATION INSTRUCTIONS

Follow flooring manufacturer's guidelines for layout, design and any special precautions for installation.

- **1. Apply product** using required tool (use a slow, smooth, even motion to achieve best results).
 - This product self-levels and will flow and pool in low spots.
 - Cure time ~8 hrs (under acceptable temperature and humidity conditions).
- 2. For gluedown, apply primer. Use Urban Surfaces' Infuse as a bond promoter before applying Urban Surfaces' adhesive (see Everlast technical data sheet for complete application instructions).

Precautionary Notes:

- If grooves, depressions or other indentations are greater than 1/8", refer to ASTM F710.
- Reseal lid when not in use to protect product.

CLEANING INSTRUCTIONS

- While product is still wet: Use a damp cloth and water to remove
- While product is still soft: Use a remover/stripper, denatured alcohol or mineral spirits. Always check compatibility on a piece of scrap flooring.

STORAGE

This product should be stored at temperatures between 50-90°F (15-32°C). PROTECT FROM FREEZING. Shelf life: 1 year.

CAUTION

DO NOT take internally. If swallowed, DO NOT induce vomiting. Call a physician immediately. KEEP OUT OF REACH OF CHILDREN. For more information, refer to Safety Data Sheet on our website (listed below).

WARRANTY INFORMATION

For warranty information, call Technical Services (toll-free) at **(800) 492-8722** and visit us online at **urbansurfaces.com**. Urban Surfaces' written pre-installation and installation instructions must be strictly followed or the Urban Surfaces warranty will be rendered void.

REQUIRED TOOLS AND COVERAGE

APPROVED INSTALLATION TYPES

TOOLS*

ESTIMATED COVERAGE**

V-Notch Trowel
gluedown, looselay, and floating floors

V-Notch Trowel
1/8" x 1/16"

~ 90-120 sqft/gal



Technical Data Sheet



	Product Classification	Unlimited Moisture Barrier, Elastomeric Membrane
	Base Chemistry	STPE Polymer-Based (Hybrid Propel®
	Curing Method	Moisture Cure
	Appearance/Color	Clear/Transluscen
	Odor	Extremely Low
	Consistency	Low Viscosity Liquid
	Application	Easy Troweling
	Flammability	Non-Flammable
	Freeze/Thaw	Protect From Freezing
	Shelf Life [Unopened Cont	ainer at 70°F] 1 Year
TESTING		
	Moisture Control	Protects Flooring from Unlimited (100% RH) Substrate Moisture Vapor Emissions
	RH [ASTM F2170]	No Testing Required (100%)
	рН	No Testing Required (5-14)
	MVER [ASTM F1869]	No Testing Required
	Porosity [ASTM F3191]	Must Pass (CSP 1+)
TIME		
	Open Time	N/A
	Flash Time	N/A
	Working Time	N/A
	Cure Time	8 hrs
TD45510	Pot Life	N/A
TRAFFIC	Light Traffic	N/A
	Heavy Traffic	N/A
ACCOUSTICS*	Rolling Loads	N/A
<u>ACCOUSTICS</u>	STC	N/A
	IIC	N/A
	Delta ΔIIC	N/A
SUSTAINABILITY		•
	Solvents	No
	Isocyanates	No
	VOC Wet Applied [g/L] [SC	AQMD Rule #1168] < 0.05 g/L
	Bio-Based Content	No
	Post-Consumer Receycled	Content
	Mineral Abundant Content	No
	LEED v4/4.1 Points	Contributes to Low Emitting Materials
	Certifications	FloorScore
	Transparency	USGBC Member
WARRANTY**	· •	
	Duration	10-Year Performance Warranty
	Coverage	100% Substrate Moisture Vapor